

Glitter Flake™

Add some extra glitter and sparkle to your design. With many colors to choose from and a unique texture this material ensures to enhance any fashion wear. Easy to cut and weed medium to small details (Polyester, 115 micron [+/- 10%]).



Glitter Flake™



FEED MATERIAL

into cutter so that the carrier is on the bottom.



CUT LOGO,

words or numbers in reverse (mirror image).

Recommended Fabrics

100% cotton
100% polyester
Poly/cotton blends

CAD-CUT® Glitter Flake™ light pink will change its appearance dramatically when heat applied onto dark colored textiles, creating exciting effects.

Due to the combination of fabrics, weaves, coatings and dyes used in the textile industry, Stahls' recommends and provides samples of our materials and medias for testing.



WEED

away excess material leaving only the desired graphic on the carrier.



PREHEAT & POSITION

Preheat garment for 10 seconds, prior to application. Position weeded design on garment with the carrier side up.

(reads left to right)

Place a Kraft Paper cover sheet over carrier before pressing.

Accessories Required

Kraft Paper or reusable cover sheet
EZ Weeder® or Tweezers

Cutting Notes

You should always test cut prior to any production run. For optimal cutting and weeding, maintain a line thickness of at least 1/8" (3mm) for lettering & logos.



HEAT APPLY

Temperature:
320°F; 160°C
Time:
10-15 seconds
Pressure:
medium-firm
#6-7 on
Hotronix®



PEEL COOL

Allow the design to cool before peeling the clear carrier.

It is best to peel carrier away from the garment as opposed to pulling the garment from the carrier.

Care Instructions

Machine wash warm using mild detergent. Do not use bleach. Dry at a normal dryer setting on household machines. Do not iron directly onto CAD-CUT® Glitter Flake™ // Glitter. (use cover sheet)

CUTTER GUIDELINES

Multi-Layered Designs

Not recommended for multi-layer applications.

Storage

Store in a cool, dry area. Avoid direct heat, sunlight and humidity.

CUTTER	BLADE	FORCE	OFFSET	SPEED
Roland GX-24	60° / 45°	160-190g / 140-180g	.25	50cm/s

All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability whatsoever in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer.

CAD-CUT, Pressure Sensitive Poly-TWILL, & Hotronix are trademarks & ® trademarks of GroupeSTAHL™ with one or more patents or patents pending.
© Stahls' International™ 2014 - All International Rights Reserved